



BEHRAN UNBLEACHED PARAFFIN WAX

TYPICAL CHARACTERISTICS

Unbleached Paraffin Wax Grade	Oil Content %wt max.	Melting Point °C	Color Max.	Penetration 0.1mm@25°C	Viscosity @ 100°C (cSt)
	ASTM D-721	ASTM D-87	ASTM D-1500	ASTM D-1321	ASTM D-445
M1	1	62-66	1	15-19	4.5-6.4
M2	2	62-66	1	15-19	4.5-6.4
M3	3	61-65	1	15-19	4.5-6.4
M5	5	60-65	1	15-19	4.5-6.4
M10	10	60-65	1	15-19	4.5-6.4
H1	1	68-71	4.5	-	6.5-8.0
H2	2	68-71	4.5	21-28	6.5-8.0
H3	3	68-71	4.5	21-28	6.5-8.0
H5	5	68-71	4.5	-	6.5-8.0
H10	10	66-69	4.5	-	6.5-8.0

Packaging

Slabs (20×50×4cm)

in carton (app.24 Kg)

Granules packed in one plastic bag in carton (app.16Kg)

